

Date:
Our Ref:
Your Ref:
Client:
Page:

27 March 2025
E-038192
Email 21 January 2025
Sparkes Will Fly Ltd
9 of 12

Washed products, washed 30x at 60°C and tumble dried

	Original mass (g)	Wet out mass (g)	Absorption capacity (ml)	Absorption capacity (%)
Tumble dried, specimen 1	27.09	267.40	240.3	887.1
Tumble dried, specimen 2	26.21	256.10	229.9	877.1
Tumble dried, specimen 3	26.13	253.87	227.7	871.6
Mean values	26.5		232.6	878.6

Washed products, washed 50x at 60°C and line dried

	Original mass (g)	Wet out mass (g)	Absorption capacity (ml)	Absorption capacity (%)
Line dried, specimen 1	26.53	251.94	225.1	849.6
Line dried, specimen 2	27.80	257.31	229.5	825.6
Line dried, specimen 3	26.54	245.66	219.1	825.6
Mean values	27.0		224.7	833.6

Washed products, washed 50x at 60°C and tumble dried

	Original mass (g)	Wet out mass (g)	Absorption capacity (ml)	Absorption capacity (%)
Tumble dried, specimen 1	27.02	231.67	204.7	757.4
Tumble dried, specimen 2	26.15	224.97	198.8	760.3
Tumble dried, specimen 3	26.04	217.40	191.4	734.9
Mean values	26.4		198.3	750.9